

Parameters

Cutoff Wavelength	< 1480 nm
Attenuation @1550nm	< 1.5 dB/km
Beat Length @633nm	< 0.9 mm
Beat Length @1550nm	< 2.2 mm
Mode Field Diameter @1550nm	6.7 ± 0.5 μm
Numerical Aperture	0.19 ± 0.02
Core/Clad Concentricity	< 1 μm
Cladding Diameter	80 ± 1 μm
Coating Diameter	128 ± 2 μm
Proof Test Level	100 kpsi

Design Parameters

Operating Wavelength	1500 - 1600 nm
Design	Tiger
Core Shape	Round
Coating Material	Dual Acrylate
Operating Temperature Range	-40 to +85°C